

**TABOREX TA 2333 HD
Yellow Catalyst Masterbatch**

Product description: Masterbatch for the use with SILON Silane crosslinkable PE-Xb Compounds TABOREX.

TABOREX TA 2333 HD contains the cross-linking catalyst to complete together with Silane Grafted TABOREX Compound a Sioplas System (PE-Xb) in yellow colour, approx. RAL 1016 and provides processing and long-term stability to the final product.

Appearance: Sulphur Yellow, opaque.

Physical form: Pellets

Application: TABOREX TA 2333 HD is a catalyst Masterbatch according to the Sioplas system for the production of pipes for sanitary and heating applications.

Addition level: Catalyst Masterbatch and graft polymer are normally being added in the ratio of 95 parts of graft to 5 parts of catalyst MB. This formulation insures optimum processing conditions and application performance of the PE-X material.

Combinations: Not necessary.

Packing: TABOREX TA 2333 HD is supplied in 25 kg bags made of a moisture barrier aluminium/PE lining.

Storage: TABOREX TA 2333 HD has to be stored in a cool and dry place. At a maximum room temperature of 25°C the storage life is one year. Storage at higher temperatures may impair the quality of the Masterbatch.



Physical Properties:	Density:	1.1 g/cm ³
	Bulk Density:	0.55 g/cm ³
	Moisture:	< 0.05 %
	MFR (190/2.16):	8 g/10 min

Above-mentioned figures are typical values obtained from a limited number of productions.